

## Density and Size Chart for Expanded Clay Aggregate

### ECA

#### ECA<sup>®</sup> (Rounds) – Expanded Clay Aggregate

ECA Size	Approx. Weight Kg.	
	Per Bag ( 50 Liters)	Per M <sup>3</sup> (1000 Liters)
<b>R 15-30mm</b>	13-16	260-320
<b>R 8-15mm</b>	14-17	280-340
<b>R 2-8mm</b>	17-20	340-400
<b>R 1-4mm</b>	33-37	660-740
<b>R 3-4mm</b>	26-29	520-580
<b>R 2-3mm</b>	29-33	580-660
<b>R 1-2mm</b>	32-36	640-720
<b>R 0-1mm</b>	40-44	800-880
<b>R 0.5-1mm</b>	36-40	720-800
<b>R 0-0.5mm</b>	38-42	760-840

#### ECA<sup>®</sup> (Crushed) – Expanded Clay Aggregate

ECA Size	Approx. Weight Kg.	
	Per Bag ( 50 Liters)	Per M <sup>3</sup> (1000 Liters)
<b>C 2-8mm</b>	14-17	280-340
<b>C 1-4mm</b>	28-32	560-640
<b>C 3-4mm</b>	19-23	380-560
<b>C 2-3mm</b>	20-24	400-480
<b>C 1-2mm</b>	25-29	500-580
<b>C 0-1mm</b>	36-40	720-800
<b>C 0.5-1mm</b>	26-30	520-600
<b>C 0-0.5mm</b>	33-37	660-740

#### ECA<sup>®</sup> (High Density Crushed) – Expanded Clay Aggregate (Construction)

ECA Size	Approx. Weight Kg.	
	Per Bag ( 50 Liters)	Per M <sup>3</sup> (1000 Liters)
<b>HDC 2-8mm</b>	28-35	560-700